



INVESTOR IN PEOPLE

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)


The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.


Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed


Dated

2 December 2004



BEST AVAILABLE COPY

Patents Form 1/77

Patents Act 1977
(Rule 16)19NOV03 08:53:152-1 00063
P01/7700 0326853.9

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference

CDT 471 GB

2. Patent application number

(The Patent Office will fill this part in)

0326853.9

19 NOV 2003

3. Full name, address and postcode of the or of each applicant (underlines all surnames)

CAMBRIDGE DISPLAY TECHNOLOGY LIMITED

GREENWICH HOUSE
MADINGLEY RISE
MADINGLEY ROAD
CAMBRIDGE CB3 0TX
b1664 41006
UNITED KINGDOM

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

4. Title of the invention

OPTICAL DEVICE

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

IP DEPARTMENT
CAMBRIDGE DISPLAY TECHNOLOGY LTD
GREENWICH HOUSE
MADINGLEY RISE
MADINGLEY ROAD
CAMBRIDGE CB3 0TX

Patents ADP number (if you know it)

06166441011

6. Priority: Complete this section if you are declaring priority from one or more earlier patent applications, filed in the last 12 months.

Country

Priority application number
(if you know it)Date of filing
(day / month / year)

7. Divisionals, etc: Complete this section only if this application is a divisional application or resulted from an entitlement dispute (see note f)

Number of earlier UK application

Date of filing
(day / month / year)

8. Is a Patents Form 7/77 (Statement of inventorship and of right to grant of a patent) required in support of this request?

YES

Answer YES if

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body.

Otherwise answer NO (see note d)

Patents Form 1/77

0086383 19 NOV 03 12:05

Patents Form 1/77

9. Accompanying documents: A patent application must include a description of the invention. Not counting duplicates, please enter the number of pages of each item accompanying this form:

Continuation sheets of this form

Description

17

Claim(s)

3

Abstract

-

Drawing(s)

2

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for a preliminary examination and search (Patents Form 9/77)

ONE

Request for a substantive examination (Patents Form 10/77)

ONE

Any other documents (please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature(s)

Date

19th NOVEMBER 2003

12. Name, daytime telephone number and e-mail address, if any, of person to contact in the United Kingdom

ANWAR GHANI TEL: 01223 723519

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500305.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered YES in part 8, a Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- Part 7 should only be completed when a divisional application is being made under section 15(4), or when an application is being made under section 8(3), 12(6) or 37(4) following an entitlement dispute. By completing part 7 you are requesting that this application takes the same filing date as an earlier UK application. If you want the new application to have the same priority date(s) as the earlier UK application, you should also complete part 6 with the priority details.

DUPLICATE

Optical Device

Field of the Invention

The invention relates to organic electroluminescent devices and methods for the forming thereof.

Background of the Invention

One class of opto-electrical devices is that using an organic material for light emission or detection. The basic structure of these devices is a light emissive organic layer, for instance a film of a poly (p-phenylenevinylene) ("PPV") or polyfluorene, sandwiched between a cathode for injecting negative charge carriers (electrons) and an anode for injecting positive charge carriers (holes) into the organic layer. The electrons and holes combine in the organic layer generating photons. In WO 90/13148 the organic light-emissive material is a polymer. In US 4,539,507 the organic light-emissive material is of the class known as small molecule materials, such as (8-hydroxyquinoline) aluminium ("Alq3"). In a practical device one of the electrodes is transparent, to allow the photons to escape the device.

A typical organic light-emissive device ("OLED") is fabricated on a glass or plastic substrate coated with a transparent first electrode such as Indium-tin-oxide ("ITO"). A layer of a thin film of at least one electroluminescent organic material covers the first electrode. Finally, a cathode covers the layer of electroluminescent organic material. The cathode is typically a metal or alloy and may comprise a single layer, such as aluminium, or a plurality of layers such as calcium and aluminium. Other layers can be added to the device, for example to improve charge injection from the electrodes to the electroluminescent material. For example, a hole injection layer such as poly(ethylene dioxythiophene) / polystyrene sulfonate (PEDOT-PSS) or polyaniline may be provided between the anode and the electroluminescent material. When a voltage is applied between the electrodes from a power supply one of the electrodes acts as a cathode and the other as an anode.

For organic semiconductors important characteristics are the binding energies, measured with respect to the vacuum level of the electronic energy levels, particularly the "highest occupied molecular orbital" (HOMO) and the "lowest unoccupied molecular


orbital" (LUMO) level. These can be estimated from measurements of photoemission and particularly measurements of the electrochemical potentials for oxidation and reduction. It is well understood in this field that such energies are affected by a number of factors, such as the local environment near an interface, and the point on the curve (peak) from which the value is determined. Accordingly, the use of such values is indicative rather than quantitative.

In operation, holes are injected into the device through the anode and electrons are injected into the device through the cathode. The holes and electrons combine in the organic electroluminescent layer to form an exciton which then undergoes radiative decay to give light.

The active organic layers of an OLED are typically formed by evaporation of the materials (in the case of small molecule materials), or by solution deposition (in the case of polymeric or dendrimeric materials). Evaporation allows formation of multiple layers, in particular hole transporting and / or electron transporting layers to assist transport of charge into the electroluminescent layer. Solution-deposited materials are less amenable to formation of such multilayers because a solution-deposited layer is prone to dissolution in the solvent used to deposit a subsequent layer.

One approach that utilises charge transporting materials for solution processable systems without requiring formation of multiple layers is disclosed in WO 99/48160 and WO 02/28983 wherein a hole transporting component, an electron transporting component and an emissive component are blended together.

Another approach entails incorporation of the charge transporting units described in WO 99/48160 into an electroluminescent polymer as described in WO 00/55927 which discloses a blue electroluminescent polymer of formula (a):



wherein $w + x + y = 1$, $w \geq 0.5$, $0 \leq x + y \leq 0.5$ and $n \geq 2$

In essence, the separate hole transporting, electron transporting and emissive components disclosed in WO 99/48160 are combined into a single molecule. Conjugated chains of the F8 repeat unit provide electron transport; the TFB unit is provided for the purpose of hole transport; and the PFB repeat unit is provided as the emissive unit. The use of a single electroluminescent polymer, rather than a blend, has been found to improve lifetime of the electroluminescent materials, in particular blue electroluminescent materials whilst retaining the improved efficiency conferred by charge transporting components (by "lifetime" is meant the time for the brightness of the OLED to halve at constant current when operated under DC drive). The combination of units into a single polymer may be preferable to a blend, for example intramolecular charge transport may be preferable to intermolecular charge transport and potential difficulties caused by undesirable forms of phase separation in blends is avoided.

Co-pending application PCT GB03/01991 describes improvement in the lifetime of polymer (a) by removal of the hole transporting "TFB" repeat unit to provide a polymer wherein both hole transport and emission is provided by the "PFB" repeat unit.

The improvement in blue lifetime in replacing blends with these unblended "single component" polymers is particularly significant because full colour OLEDs require red, green and blue emissive materials however, in spite of the aforementioned developments, blue emissive materials known to date still suffer from relatively short lifetime in comparison to red and green materials.

It is therefore an object of the present invention to provide an electroluminescent device, in particular an electroluminescent device comprising a blue emitter, having improved lifetime.

Summary of the invention

The present inventors have surprisingly found that deposition of a blend comprising a hole transporting material and an electroluminescent material containing a hole transporting unit provides improved lifetime.

Accordingly, in a first aspect the invention provides a method of forming an electroluminescent device comprising the steps of:

- providing a substrate comprising a first electrode for injection of charge carriers of a first type
- forming a semiconducting region by depositing onto the substrate a composition comprising a first material for transporting charge carriers of the first type and a second material for emission and transporting charge carriers of the first type; and
- depositing over the semiconducting region a second electrode for injection of charge carriers of a second type.

By "hole transporting material" is meant a material capable of transporting holes from a hole injecting material to an electroluminescent material. Preferably, the HOMO of the hole transporting material is less than 0.7 eV, more preferably less than 0.5 eV, most preferably less than 0.2 eV, from the HOMO of the anode or hole injecting material. A typical electroluminescent device comprises an anode having a workfunction of 4.8 eV.


Accordingly, the HOMO level of hole transporting materials is preferably around 4.8-5.5 eV. Similarly, the cathode of a typical device will have a workfunction of around 3 eV. Accordingly, the LUMO level of electron transporting materials is preferably around 3-3.5 eV. The emissive segment of the second material is determined by the component of the second material having the smallest HOMO-LUMO bandgap.

Preferably, the first electrode is an anode; the second electrode is a cathode; the charge carriers of the first type are holes and the charge carriers of the second type are electrons.

The second material may comprise separate charge transporting and emissive regions or units. Alternatively, both of the functions of charge transport and emission may be provided by the same region or unit of the emissive material.

Preferably, at least one (and more preferably both) of the first material and second material are polymers, more preferably conjugated polymers.


Preferably, the first material comprises an optionally substituted repeat unit of formula (I):



(I)

wherein each Ar is independently selected from optionally substituted aryl or heteroaryl.

Preferably, each Ar is optionally substituted phenyl. More preferably, the first repeat unit comprises an optionally substituted repeat unit of formula (II):




(II)

wherein each R is selected from hydrogen or a substituent. Preferred substituents R include solubilising groups, such as alkyl or alkoxy groups, and groups for modifying the electron affinity of the repeat unit, such as electron withdrawing groups.

Preferably, the repeat unit of formula (II) comprises a single nitrogen atom in its backbone.


Preferably, the second material is a polymer comprising an optionally substituted repeat unit of formula (III):



(III)

wherein each Ar¹ independently represents an optionally substituted aryl or heteroaryl.

Preferably, each Ar¹ is optionally substituted phenyl. More preferably, the first repeat unit comprises an optionally substituted repeat unit of formula (IV):




(IV)

wherein R is as defined above.

Preferably, at least one (more preferably both) of the first and second materials are polymers comprising a further repeat unit selected from optionally substituted fluorene, spirofluorene, indenofluorene, phenylene or oligophenylene, preferably fluorene, more preferably 9,9-disubstituted fluorene-2,7-diyl.

Particularly preferred further repeat units are selected from optionally substituted repeat units of formula (V):



(V)

wherein each R^1 is independently selected from optionally substituted alkyl, alkoxy, aryl and heteroaryl. Particularly preferred substituents R^1 are selected from branched or linear C_{1-10} alkyl and hydrocarbyl aryl.

Particularly preferred further repeat units are optionally substituted 9,9-dialkyl- or 9,9-dialkoxy-2,7-fluorenyl, most preferably 9,9-di(n-octyl)fluorene.

Preferably, the second material is capable of electroluminescence in the wavelength range 400-500 nm, most preferably 430-500 nm.

Preferably, the first material : second material ratio is in the range 5:95 – 30:70, more preferably 10:90 – 20:80.

Preferably, the composition is deposited from a solution in a solvent.

The solvent for the composition may be a single solvent or a blend of two or more solvents. Preferably, the solvent comprises a substituted benzene, more preferably a mono- or poly-alkylated benzene.

In a second aspect, the invention provides an electroluminescent device obtainable by the method according to the first aspect of the invention.

Brief Description of the Drawings

The present invention will now be described in further detail, by way of example only, with reference to the accompanying drawings in which:

FIGURE 1 shows a prior art electroluminescent device

FIGURE 2 shows a comparative data of voltage required for a luminance of 100 cd / m² for a variety of electroluminescent systems.

Detailed Description of the Invention

With reference to Figure 1, the standard architecture of an optical device according to the invention, in particular an electroluminescent device, comprises a transparent glass or plastic substrate 1, an anode of indium tin oxide 2 and a cathode 4. A semiconducting region is located 3 between anode 2 and cathode 4.

Semiconducting region 3 may comprise the first and second materials according to the invention alone, or may comprise further materials. The first and second materials are preferably deposited from solution in the form of a blend, which may undergo partial or total phase separation upon evaporation of the solvent. If the first or second materials do not provide one of the functions of hole transport or electron transport, then a further material providing this function may be included in semiconducting region 3 either as a separate material blended with the first and second materials as disclosed in WO 99/48160 or as unit incorporated into the first or second material, in particular a repeat unit of a polymer as disclosed in WO 00/55927. The further material may also be provided as a separate layer within semiconducting region 3.

Where the second material is a polymer, its functions of emission and charge transport may be provided by regions comprising a single repeat unit with the polymer or by a chain of repeat units, such as a conjugated chain of polyfluorene units functioning as an electron transporting region. The different regions within such a polymer may be provided along the polymer backbone, as per US 6353083, or as groups pendant from the polymer backbone as per WO 01/62889.

Where the first and second materials are polymers, they are preferably copolymers comprising an arylene or heteroarylene co-repeat unit such as a fluorene, particularly 2,7-linked 9,9 dialkyl fluorene or 2,7-linked 9,9 diaryl fluorene; a spirofluorene such as 2,7-linked 9,9-spirofluorene; an indenofluorene such as a 2,7-linked indenofluorene; or a phenyl such as alkyl or alkoxy substituted 1,4-phenylene. Each of these groups may be substituted.

Further suitable arylene or heteroarylene groups are known in this art, for example as disclosed in WO 00/56927 and WO 00/46321, the contents of which are incorporated herein by reference.

Each such polymer may be a homopolymer, copolymer, terpolymer or higher order polymer. These copolymers, terpolymers or higher order polymers include regular alternating, random and block polymers where the percentage of each monomer used to prepare the polymer may vary.

For ease of processing, it is preferred that the first and second materials are soluble. Substituents such as C₁₋₁₀ alkyl or C₁₋₁₀ alkoxy may be selected to confer solubility on the

polymer in a particular solvent system. Typical solvents include mono- or poly-alkylated benzenes such as toluene and xylene or solvents such as tetrahydrofuran.

Suitable techniques for depositing solutions of the first and second materials include inkjet printing as disclosed in EP 0880303, spin-coating, dip-coating and doctor blade coating.

Two polymerisation techniques that are particularly amenable to preparation of conjugated polymers from aromatic monomers are Suzuki polymerisation as disclosed in, for example, WO 00/53658 and Yamamoto polymerisation as disclosed in, for example, "Macromolecules", 31, 1099-1103 (1998). Suzuki polymerisation entails the coupling of halide and boron derivative functional groups; Yamamoto polymerisation entails the coupling of halide functional groups. Accordingly, it is preferred that each monomer is provided with two reactive functional groups P wherein each P is independently selected from the group consisting of (a) boron derivative functional groups selected from boronic acid groups, boronic ester groups and borane groups and (b) halide functional groups.

Although not essential, a layer of organic hole injection material (not shown) between the anode 2 and the polymer layer 3 is desirable because it assists hole injection from the anode into the layer or layers of semiconducting polymer. Examples of organic hole injection materials include poly(ethylene dioxythiophene) (PEDT / PSS) as disclosed in EP 0901178 and EP 0947123, or polyaniline as disclosed in US 5723873 and US 5798170.


Cathode 4 is selected from materials that have a workfunction allowing injection of electrons into the electroluminescent layer. Other factors influence the selection of the cathode such as the possibility of the adverse interactions between the cathode and the electroluminescent material. The cathode may consist of a single material such as a layer of aluminium. Alternatively, it may comprise a plurality of metals, for example a bilayer of calcium and aluminium as disclosed in WO 98/10621, elemental barium disclosed in WO 98/57381, Appl. Phys. Lett. 2002, 81(4), 634 and WO 02/84759 or a thin layer of dielectric material to assist electron injection, for example lithium fluoride disclosed in WO 00/48258 or barium fluoride, disclosed in Appl. Phys. Lett. 2001, 79(5), 2001.

Electroluminescent displays according to the invention may be monochrome displays or full colour displays (i.e. formed from red, green and blue electroluminescent materials). An electroluminescent device according to the invention may also be used for lighting, in particular as a source of white light. For example, the device may comprise a blue electroluminescent polymer with means for downconverting a portion of the blue polymer by means of red and green downconverters in order to produce white light from a blend of red, green and blue emission as disclosed in, for example, US 6515314 wherein downconversion is provided by nanoparticles located within the layer of emissive material or Applied Physics Letters 80(19), 3470-3472, 2002 wherein downconverter particles are attached to the outer surface of the substrate of the device.

Examples


Monomer Examples

Monomers according to the invention were prepared in accordance with the scheme below:



Monomer Example M1: 2,7-dibromo-9,9-diphenylfluorene


2,7-Dibromofluorenone



In a 3L flange flask fluorenone (100.006g, 0.555 mol), phosphorus pentoxide (110.148g, 0.776 mol) and trimethylphosphate (1200 mL) were mixed. Under mechanical stirring, a solution of bromine (63 mL, 1.23 mol) in trimethylphosphate (200 mL) was quickly added. This clear solution was then heated for 22 hours at 120 °C. The mixture was allowed to cool to room temperature, then poured into 3L of water. When sodium thiosulfate was added (50.045g) the mixture turned yellow. Stirring was maintained for 1 hour then the yellow solid was filtered. This solid was heated in methanol to remove the mono-brominated compound and gave 176.183g (98% pure by HPLC, 94% yield).


¹H NMR (CDCl₃) 7.73 (2H, d, J 2.0), 7.61 (2H, dd, J 7.6, 2.0), 7.36 (2H, d, J 8.0); ¹³C NMR (CDCl₃) 142.3, 137.5, 135.3, 127.9, 123.3, 121.8, 109.8.

4,4'-Dibromo-2-carboxylic acid-1, 1'-biphenyl




In a 2L flange flask 2,7-dibromofluorenone (120.528g, 0.356 mol), potassium hydroxide (finely powdered flakes, 168.327g, 3.000 mol) and toluene (600 mL) were placed. This mixture was heated at 120 °C for four hours then left to cool to room temperature. Water was added to dissolve the solid (~ 2L) under vigorous stirring. The greenish aqueous layer was removed and the yellow toluene layer was washed twice with water. The combined aqueous layers were acidified with concentrated hydrochloric acid then the precipitated solid was filtered, dried then recrystallised from toluene to give 100.547g of off white crystals (79% yield): ¹H NMR ((CD₃)₂CO) 8.00 (1H, d, J 2.0), 7.77 (1H, dd, J 8.0, 2.4), 7.57 (2H, d, J 8.0), 7.34 (1H, d, J 8.4), 7.29 (2H, d, J 8.8) ; ¹³C NMR ((CD₃)₂CO) 167.1, 140.4, 139.8, 134.2, 133.5, 132.8, 132.7, 131.2, 130.6, 121.4, 121.1.

Methyl ester of 4,4'-dibromo-2-carboxylic acid -1,1'-biphenyl




4,4'-dibromo-2-carboxylic acid biphenyl (171.14g, 0.481 mol) was suspended in methanol (700 mL) and sulfuric acid (15 mL) then heated at 80 °C for 21 hours. The solvent was removed and the oil was dissolved in ethyl acetate. This solution was washed with 2N sodium hydroxide, water, saturated sodium chloride, dried over magnesium sulfate, filtered and evaporated to give an orange oil. This oil was treated with hot methanol, on cooling the ester precipitated out and was filtered. The mother liquor was evaporated and the solid recrystallised giving additional product. The ester was 100% pure by GCMS, a yield of 123.27g (69%) was obtained; ^1H NMR (CDCl_3) 7.99 (1H, d, J 2.0), 7.64 (1H, dd, J 8.0, 1.6), 7.51 (2H, d, J 8.4), 7.19 (1H, d, J 8.8), 7.13 (2H, d, J 8.8), 3.67 (3H, s); ^{13}C NMR (CDCl_3) 167.1, 140.3, 139.1, 134.4, 132.9, 132.1, 132.0, 131.3, 129.8, 121.9, 121.5, 52.3; GCMS: $M^+ = 370$

4,4'-dibromo-2-diphenyl alcohol -1,1'-biphenyl



4,4'-dibromo-2-methyl ester-biphenyl (24.114g, 65.1 mmol) was dissolved in dry diethyl ether (120 mL) and the solution was cooled to -60 °C by using an isopropanol/dry ice bath. Phenyl lithium (1.8M solution in cyclohexane-ether, 91 mL) was then added dropwise. The mixture was stirred and let to warm to room temperature. The reaction was complete after four hours. Water was added (70 mL) then the aqueous layer washed once with diethyl ether. Combined organic phases were washed with sodium chloride, dried over magnesium sulfate, filtered and evaporated to give a yellow powder. Recrystallisation from isopropanol afforded 19g of white solid (59% yield); GC-MS (m/z , relative intensity %) 494 (M^+ , 100); ^1H NMR (CDCl_3) 7.43 (1H, dd, J 8.4, 2.4), 7.28 (6H, m), 7.23 (2H, d, J 8.0), 7.11 (4H, m), 6.99 (1H, d, J 2.4), 6.94 (1H, d, J 8.4), 6.61 (2H, d, J 8.4); ^{13}C NMR (CDCl_3) 147.5, 146.7, 140.3, 139.3, 134.0, 133.0, 131.2, 131.1, 130.3, 128.2, 128.1, 127.8, 121.8, 121.3, 83.2.

2,7-dibromo-9,9-diphenylfluorene

The alcohol (69.169g, 140mmol) and glacial acetic acid (450ml) were stirred and heated to reflux, then concentrated hydrochloric acid (0.5ml) was added dropwise. When the addition was completed the mixture was heated for one hour and then cooled. The reaction mixture was poured into water (600ml), after which the solid was filtered off. The white solid was recrystallised from *n*-butyl acetate three times to give 20.03g of desired product (99.59% by HPLC, 30% yield).



¹H NMR (CDCl₃), δ /ppm: 7.58 (2H, d, J 7.6), 7.49 (2H, d, 1.2), 7.48 (2H, dd, 1.6), 7.25 (6H, m), 7.14 (4H, m).

¹³C NMR (CDCl₃), δ /ppm: 153.2, 144.6, 138.3, 131.1, 129.6, 128.7, 128.2, 127.4, 122.0, 121.7, 65.8.

Monomer Examples M2-M4


Monomers with Ar groups as detailed in the table below were prepared in accordance with the scheme and general experimental process outlined above. Aryllithium compounds corresponding to Ar groups shown in the table were prepared from the corresponding aryl bromide.

Monomer example no.	Ar	Yield of monomer
M2		90%

M3		24%
M4		22%

Polymer Example P1

A blue electroluminescent polymer according to the invention was prepared in accordance with the process of WO 00/53656 by reaction of 9,9-di-n-octylfluorene-2,7-di(ethylenylboronate) (0.65 equivalents), 2,7-dibromo-9,9-diphenylfluorene (0.30 equivalents) and N,N'-di(4-bromophenyl)-N,N'-di(4-n-butylphenyl)-1,4-diaminobenzene (0.05 equivalents) to give polymer P1:



Device Example

General procedure

Onto indium tin oxide supported on a glass substrate (available from Applied Films, Colorado, USA) was deposited a layer of PEDT / PSS, available from Bayer ® as Baytron P ® by spin coating. A solution of a blend of TFB and polymer P1 were deposited over the PEDT / PSS layer by spin-coating. Onto the polymer P1 was deposited by evaporation a cathode consisting of a first layer of barium and a second, capping layer of aluminium.

Lifetime

Devices according to the invention were made according to the general procedure using a range of P1:TFB ratios and different solvents. For the purposes of comparison, a device comprising no TFB was made. In each case, at least two devices were made. Devices were driven at 800 cd / m².

P1 : F8-TFB ratio	Deposition solvent	Lifetime (hours)
80:20	ortho-xylene	74, 77, 78
95:5	ortho-xylene	69, 91, 79
80:20	anisole:cyclohexylbenzene 50:50	107, 95
100:0 (comparative)	o-xylene	21, 16

As can be seen from the results, lifetime of devices comprising a blend according to the invention show around a four- to five-fold increase in lifetime. The effect of using a different solvent on lifetime indicates that phase separation effects in the blend play a role in determining device performance. The improvement in lifetime of P1 by blending with F8-TFB copolymer is surprising given that removal of TFB units from polymer (a) described above was previously found to improve lifetime, and given that unblended polymers have previously been found to afford superior lifetimes as compared to blended polymers. Without wishing to be bound by any theory, it is believed that the blend according to the invention undergoes vertical phase separation such that F8-TFB copolymer migrates towards the anode side of the device which would, in effect, result in formation of a hole transporting layer of F8-TFB located between the anode and the electroluminescent layer which would also act to serve as a barrier against ingress of impurities from ITO and / or PEDOT into the electroluminescent material. Deposition of a hole transporting layer followed by an electroluminescent layer is well known in the art, however the present invention enables formation of a hole transporting layer and an electroluminescent layer in a one-step process. Furthermore, the present invention takes advantage of phase-separation effects in order to, in effect, form a multilayer device thus overcoming the aforementioned difficulty in forming multilayers of solution processable materials.

Drive Voltage


As can be seen from Figure 2, a reduction in drive voltage is achieved for the blended systems according to the invention as compared to the control. A reduction is obtained across a range of different TFB : Polymer 1 ratios and for different solvents.

Quantum efficiency

Example	Solvent	Maximum quantum efficiency (%)	Quantum efficiency @ 100 cd/m ² (%)
Comparative polymer	ortho-xylene	0.6	0.4
P1:TFB 100:0 (comparative)	ortho-xylene	2.4	2.25
P1:TFB 80:20	ortho-xylene	3.0	2.3
P1:TFB 80:20	anisole:cyclohexylbenzene 50:50	3.2	2.4

As can be seen, there is a significant increase in maximum quantum efficiency for blended systems according to the invention as compared to polymer P1 alone, as well as a marginal increase in quantum efficiency at 100 cd / m². More notable is the effect of removing the "TFB" repeat unit from the comparative polymer (structure shown below) to give polymer P1, and providing the "TFB" component as a separate material rather than as a component of the same polymer.

Comparison of devices containing polymers C1 and P1 alone show that removal of "TFB" repeat units from polymer C1 results in a significant improvement in performance. In view of this, it is surprising that the inclusion of "TFB" in the form of the hole transporting material F8-TFB should improve device performance, and again indicates the advantageous effect of phase separation.




Comparative polymer C1

Although the present invention has been described in terms of specific exemplary embodiments, it will be appreciated that various modifications, alterations and / or combinations of features disclosed herein will be apparent to those skilled in the art without departing from the spirit and scope of the invention as set forth in the following claims.

Claims


- 1) A method of forming an electroluminescent device comprising the steps of:
- providing a substrate comprising a first electrode for injection of charge carriers of a first type
 - forming a semiconducting region by depositing onto the substrate a composition comprising a first material for transporting charge carriers of the first type and a second material for emission and transporting charge carriers of the first type; and
- depositing over the semiconducting region a second electrode for injection of charge carriers of a second type.
- 2) A method according to claim 1 wherein the first electrode is an anode; the second electrode is a cathode; the charge carriers of the first type are holes and the charge carriers of the second type are electrons.
- 3) A method according to claim 1 or 2 wherein at least one of the first material and second material are polymers, more preferably conjugated polymers.
- 4) A method according to claim 3 wherein the first material comprises an optionally substituted repeat unit of formula (I):



(I)

wherein each Ar is independently selected from optionally substituted aryl or heteroaryl.


- 5) A method according to claim 4 wherein each Ar is optionally substituted phenyl.
- 6) A method according to claim 5 wherein the first repeat unit comprises an optionally substituted repeat unit of formula (II):



(II)

wherein each R is selected from hydrogen or a substituent.


- 7) A method according to claim 6 wherein the repeat unit of formula (II) comprises a single nitrogen atom in its backbone.
- 8) A method according to any one of claims 3-7 wherein the second material is a polymer comprising an optionally substituted repeat unit of formula (III):



(III)

wherein each Ar¹ independently represents an optionally substituted aryl or heteroaryl.


- 9) A method according to claim 8 wherein each Ar¹ is optionally substituted phenyl.
- 10) A method according to claim 9 wherein the first repeat unit comprises an optionally substituted repeat unit of formula (IV):



(IV)

wherein R is as defined in claim 6.

- 11) A method according to any one of claims 3-10 wherein at least one of the first and second components is a polymer comprising a further repeat unit selected from optionally substituted fluorene, spirofluorene, indenofluorene, phenylene or oligophenylene, preferably fluorene, more preferably 9,9-disubstituted fluorene-2,7-diyl.
- 12) A method according to claim 11 wherein the further repeat unit is selected from optionally substituted repeat units of formula (V):



- wherein each R¹ is independently selected from optionally substituted alkyl, alkoxy, aryl and heteroaryl, and the two groups R¹ may be linked.
- 13) A method according to any preceding claim wherein the second material is capable of electroluminescence in the wavelength range 400-500 nm, most preferably 430-500 nm.
- 14) A method according to any preceding claim wherein the first material : second material ratio is in the range 5:95 – 30:70, more preferably 10:90 – 20:80.
- 15) A method according to any preceding claim wherein the composition is deposited from a solution in a solvent.
- 16) A method according to claim 15 wherein the solvent comprises a substituted benzene.
-
- 17) A method according to claim 16 wherein the solvent comprises a mono- or poly-alkylated benzene.
- 18) An electroluminescent device obtainable according to the method of any preceding claim.

Figure 1





Figure 2



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record.**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☒ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.



Creation date: 08-04-2006
Indexing Officer: MLEE1 - MARINA LEE
Team: OIPEBackFileIndexing
Dossier: 10596061

Legal Date: 05-26-2006

No.	Doccode	Number of pages
1	371P	5
2	SPEC	14
3	CLM	7
4	ABST	2
5	ABST	2
6	DRW	14
7	FRPR	21

Total number of pages: 65

Remarks:

Order of re-scan issued on